

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : B29C 47/06, 49/04	A1	(11) International Publication Number: WO 93/10956 (43) International Publication Date: 10 June 1993 (10.06.93)
<p>(21) International Application Number: PCT/US91/08985</p> <p>(22) International Filing Date: 27 November 1991 (27.11.91)</p> <p>(71) Applicant: GENERAL ELECTRIC COMPANY [US/US]; 1 River Road, Schenectady, NY 12345 (US).</p> <p>(72) Inventors: COYLE, Dennis, Joseph ; 9 Jonathan Drive, Clifton Park, NY 12065 (US). TEUTSCH, Erich, Otto ; RR 3, Summit Road, Pittsfield, MA 01201 (US).</p> <p>(74) Agents: KING, Arthur; Counsel, International Patent Operation, General Electric Company, 1285 Boston Avenue, Bldg. 23CW, Bridgeport, CT 06602 (US) et al.</p>	<p>(81) Designated States: JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LU, NL, SE).</p> <p>Published With international search report.</p>	

(54) Title: MODULAR TUBULAR EXTRUSION HEAD AND A PROCESS FOR EXTRUDING TUBULAR ARTICLES

(57) Abstract

A polymer resin extrusion head includes one or more annular extrusion modules in which a spiral channel means having one or more convolutions extends from a resin inlet on the periphery of the module to an annular extrusion outlet. Preferably, the channel means gradually opens into an annular frustoconical space leading to the extrusion outlet at the inner edge of the module. The spiral channel extends symmetrically around the extrusion module or modules in a manner so as to subject all of the extruded polymer flowing from the inlet to the extrusion outlet to substantially the same process conditions along the flow path. As a result, the polymer is distributed at the outlet with properties which are substantially symmetrical around the axis of the extrusion module or modules for all resin distributed to the outlet. It is preferable that the extrusion module or modules comprise a pair of mating annular members with central frustoconical portions having apexes with an axial dimension greater than the axial dimension of the outer portions of the modules so as to form air spaces around each module including frustoconical air space portions to avoid direct heat transfer between adjacent modules.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

MODULAR TUBULAR EXTRUSION HEAD AND A PROCESS
FOR EXTRUDING TUBULAR ARTICLES

BACKGROUND OF THE INVENTION

Related Application

5 This application is a continuation-in-part application of Serial No. 535,452, filed September 20, 1990, for a "MODULAR TUBULAR EXTRUSION HEAD".

Field of the Invention

10 The invention relates to resin extrusion apparatus and particularly to extrusion heads for producing articles with one or more tubular layers such as parisons, wire coatings, blown films, pipes, pultruded rods, profiles, reinforced sheets, etc.

Description of Prior Art

15 Parisons, tubular extrusions of plastic resin which are subsequently blow molded to form bottles or other containers, are formed in the prior art by various apparatus some including extrusion heads which extrude successive layers of plastic resin onto a
20 mandrel. A typical multilayer parison extrusion head has separate inlets for receiving heated and plasticized resin from individual screw extruders and has separate channels for distributing and expressing the respective plastic resins in successive layers on

the mandrel. Each channel includes an annular equalization and distribution chamber surrounding and spaced from the mandrel for receiving the plastic resin from the corresponding inlet. From the equalization chamber the plastic resin is fed through a frustoconical transfer passage downward and inward to a tubular extrusion channel formed around the mandrel. This annular extrusion channel exits through an inwardly or outwardly flaring annular die which includes a conical core member which may be moved longitudinally relative to the outer member of the die to vary the thickness of the wall of the extruded tubular article.

One particularly useful and successful extrusion head for forming tubular articles such as parisons is disclosed in U.S. Patent No. 4,798,526. This head includes one or more individual annular extrusion modules surrounding respective successive portions of a stepped or tapered mandrel to form the annular extrusion channel which receives one or more successively extruded plastic resin layers from the modules. Each module has a pair of members with mating surfaces wherein the equalization and distribution chamber and the frustoconical transfer passage are formed. Having the head formed from individual coaxially spaced extrusion modules enables the head to be readily assembled and disassembled as well as enabling the assembly of an extrusion head with varying numbers of modules so that a module can be used in one assembled head to extrude a single layer tubular article or can be used in a differently assembled head to extrude any layer of a multilayer article. The modules forming an extrusion head can be positioned in any desired order. Furthermore, the die modules are separated from each other by annular air spaces.

Concentric tubular necks or collars extend from each module into engagement with an adjacent module to define the separation distance or the width of the air spaces between modules. These air spaces prevent heat transfer from a high temperature module to an adjacent low temperature module. Low temperature resins can be degraded if heated to the higher temperature. This patent further discloses polymer inlet pressures at the extrusion head of 4,000 to 6,000 psi (27,000 to 41,000 KPa) for polycarbonate, 2,500 to 4,000 psi (17,000 to 28,000 KPa) for polypropylene, and 2,000 to 3,000 psi (13,000 to 21,000 KPa) for tie resins and barrier resins.

U.S. Patents No. 3,649,143, No. 4,111,630 and No. 4,182,603 disclose tubular extrusion dies for blow molding of multi-ply films and having nested frustoconical, hemispherical and cylindrical die members forming polymer distribution chambers wherein spiral and helical grooves are formed on the outer surfaces of inner members. These grooves progress from points near or at the inlets toward the outlets with decreasing depth so that the polymer flow is gradually forced out of the grooves and into the frustoconical, hemispherical or tubular space between die members to evenly distribute the polymer around the chamber. These nested arrangements have several deficiencies such as limiting any temperature differential between the different layers being extruded, requiring larger heads for extruding greater numbers of layers, and having long conical passages from the end of the groove or grooves to the annular outlet.

Generally the prior art tubular extrusion apparatus requires a restrictive frustoconical transfer passage from the distribution chamber to the annular

outlet from which the tubular article is extruded. This restrictive passage provides a relatively large pressure drop, i.e., greater than 50% of the total pressure drop from the extrusion head inlet through the distribution region or chamber and the restrictive passage to the outlet, in order to assist in even distribution of the polymer in the distribution chamber. In the absence of the restrictive outlet passage with the relatively large pressure drop, the polymer tends to flow at a greater rate along the shortest path between the inlet to the distribution chamber and the closest region of the annular outlet producing unevenness in the thickness of the tubular article about its circumference.

While the prior art apparatus is generally efficient and successful in the extrusion of tubular articles such as multilayer parisons, blown films, wire coatings, etc., there is room for improvement. In addition to the pressure differential problems discussed above, the stresses caused by temperature differentials need to be reduced. For instance, polymer melt in prior art extrusion heads flow from the inlet side of an equalization and distribution chamber to the opposite side. As a result, resins processed in prior art extrusion heads are subjected to temperature differentials, as well as subjected to the above-described pressure differentials, as the resin is processed through the inlet, the distribution means, and outlet. As a result of these processing differentials, the resin extrudate will deposit in a non-homogeneous distribution, thereby creating actual and latent internal stresses in the extruded parison. Then when the parison is formed into a final shape of a bottle or similar container, such internal stresses

will be carried forward, and perhaps in some instances even exacerbated, in the final product. For instance, if the bottle or like article is to be reused and subjected to high temperature cleaning or the like and
5 filled under pressure, e.g., with carbonated beverage, the article may explode as a result of such internal stresses. Given that prior extrusion apparatus are likely unable to alleviate these stresses there is a need to further improve extrusion heads. This is
10 especially so in light of environmental demands which require reuse of containers rather than their disposal in landfills or the like.

Accordingly an object of the present invention is to construct a new and improved polymer extrusion head
15 and process for tubular extrusions which minimize processing differentials that occur in prior art extrusion heads and processes and thereby resulting in a more homogenous distribution of polymer as it is extruded.

20 It is also an object of the invention to provide a container having superior properties as a result of the improved polymer distribution described above, and to thereby provide a container having sufficient properties to be effectively and safely reused or
25 reclaimed.

SUMMARY OF THE INVENTION

The present invention provides a process for extruding containers which achieves the above described object, the process comprising

30 disposing and securing an extrusion module or modules along a longitudinal axis;

said extrusion module or modules each having a resin inlet, a bore having an inner cylindrical

- surface, and an annular extrusion outlet opening into said inner cylindrical surface;
- 5 each of said module or modules having channel means for receiving and distributing resin extending from the inlet to the outlet and defining a flow path for the polymer to flow from the inlet to the annular extrusion outlet through which the polymer is extruded
- 10 in annular form, said channel means extending symmetrically around the longitudinal axis of said extrusion module or modules in a manner so as to subject all of the polymer flowing from said inlet to said outlet to substantially the same process
- 15 conditions along said flow path whereby the polymer is distributed at the annular outlet with properties which are substantially symmetrical around the axis for all resin distributed through the module or modules from introducing a polymer material into said inlet and flowing said polymer through the module or modules from the inlet and through said flow path to said extrusion outlet so that the flowing polymer material
- 20 substantially circumscribes the axis for all extrusion outlet with properties which are substantially symmetrical around the axis for all polymer flowing through the module or modules; extruding the polymer material through said
- 25 extrusion channel; forming a parison from the polymer material as it exits the extrusion channel, and molding a container from the parison so formed, whereby said container is formed substantially free of internal stresses which otherwise result from peripheral variations in the properties of the extruded polym r around the p riphery of said parison.
- 30

In one embodiment, the above process can be carried out with a polymer resin extrusion head for extruding tubular articles, comprising

one or more annular extrusion modules disposed
5 along a longitudinal axis of the module or modules;
means for holding the annular extrusion module or modules along the axis;

the extrusion module or modules each having a polymer inlet, a bore having an inner cylindrical
10 surface, and an annular extrusion outlet opening into the inner cylindrical surface;

each of said module or modules having channel means for receiving and distributing polymer extending from the inlet to the outlet and defining a flow path
15 for the polymer to flow from the inlet to the annular extrusion outlet through which the polymer is extruded in annular form, said channel means extending symmetrically around the longitudinal axis of said extrusion module or modules in a manner so as to
20 subject all of the polymer flowing from said inlet to said extrusion outlet to substantially the same process conditions along said flow path whereby the polymer is distributed at the annular extrusion outlet with properties which are substantially symmetrical around
25 the axis for all resin distributed through said outlet.

In another aspect, the invention is summarized by a polymer resin extrusion head for extruding tubular articles, comprising

one or more annular extrusion modules disposed
30 along a longitudinal axis of the module or modules;
means for holding the annular extrusion module or modules along the longitudinal axis each extrusion module or modules having a pair of mating coaxial

annular members, and means securing the pair of mating annular members together;

the pair of mating annular members defining a resin inlet on the periphery of the module, a coaxial bore having an inner cylindrical surface, an annular extrusion outlet opening into the cylindrical surface;

each pair of mating annular members having channel means formed on mating surfaces of the mating annular members for receiving and distributing resin from the inlet to the annular extrusion outlet and defining a flow path for the polymer to flow from the inlet to the annular extrusion outlet through which the polymer is extruded in annular form, said channel means extending symmetrically around the longitudinal axis of said extrusion module or modules in a manner so as to subject all of the polymer flowing from said inlet to said extrusion outlet to substantially the same process conditions along said flow path whereby the polymer is distributed at the annular extrusion outlet with properties which are substantially symmetrical around the axis for all resin distributed through said outlet;

the pair of mating members having inner and outer nested frustoconical portions, respectively, with the outlet defined by an annular space between the frustoconical portions; and

the inner frustoconical portion having an inside surface with a greater angle from the axis than the angle of an outside surface of the outer frustoconical portion.

In still another aspect, the invention is summarized in polymer resin extrusion head for extruding multilayer tubular articles comprising

a plurality of coaxial annular extrusion modules disposed along a longitudinal axis;

means for holding the modules spaced longitudinally along the axis of the modules;

each module having a pair of mating coaxial annular members, and means securing the pair of mating annular members together;

the pair of mating annular members defining a resin inlet on the periphery of the module, a coaxial bore having an inner cylindrical surface, an annular extrusion outlet opening into the cylindrical surface;

each of said module or modules having channel means for receiving and distributing polymer extending from the inlet to the outlet and defining a flow path for the polymer to flow from the inlet to the annular extrusion outlet through which the polymer is extruded in annular form, said channel means extending symmetrically around the longitudinal axis of said extrusion module or modules in a manner so as to subject all of the polymer flowing from said inlet to said extrusion outlet to substantially the same process conditions along said flow path whereby the polymer is distributed at the annular extrusion outlet with properties which are substantially symmetrical around the axis for all resin distributed through said outlet; and

each module further having a center portion which is frustoconical wherein the frustoconical center portion at the center bore has a dimension along the axis which is greater than the axial dimension of the outer portions of each module so that the apex of each preceding module engages the succeeding adjacent module to form air spaces including frustoconical air space portions between adjacent modules to produce enhanced temperature isolation between modules.

In another aspect, the invention is a polymer extrusion head for extruding multilayer tubular articles comprising

an elongate mandrel;

5 a plurality of coaxial annular extrusion modules spaced longitudinally along the mandrel and extending around successive sections of a mandrel so as to define a tubular extrusion channel between the modules and the mandrel for receiving successive layers extruded by the
10 modules into the tubular extrusion channel;

an annular die mounted downstream from the extrusion modules and having three successive sections for receiving and forming the multilayered tubular extrusion from extrusion channel, the first section
15 having a tapered diameter progressively reduced from the diameter of the annular extrusion channel, the second section having a constant diameter equal to the exit diameter of the first section throughout its length, and the third section having a flared diameter
20 progressively increasing the diameter from the diameter of the second section to a desired diameter.

Other objects, advantages and features of the invention will be apparent from the following description of the preferred embodiment taken in
25 conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a section view of an extrusion head for extruding a multilayer parison in accordance with the invention.

30 Fig. 2 is a bottom view of an upper member of one extrusion module in the head of Fig. 1.

Fig. 3 is a sectional view, taken at line 3-3 of Fig. 2, of an extrusion module removed from the head of Fig. 1.

Fig. 4 is a sectional view, taken at line 4-4 of Fig. 2, of a portion broken away from the module of Fig. 3.

Fig. 5 is an elevational view, partially in section, of a broken away portion of an upper member of the module of Fig. 3 with the section taken at line 5,6 - 5,6 of Fig. 2.

Fig. 6 is an elevational sectional view of a broken away portion of a lower member of the module of Fig. 3 with the section taken at line 5,6 - 5,6 of Fig. 2.

Fig. 7 is a diagrammatic view of a parison extrusion apparatus including the extrusion head of Fig. 1.

Fig. 8 is a view similar to Fig. 2 showing a variation of the spiral channel in the upper member of the extrusion module.

Fig. 9 is a view similar to Figs. 2 and 6 showing another variation of the spiral channel in the upper member of the extrusion module.

Fig. 10 is a schematic illustration of a container blow molding process and apparatus which can incorporate an extrusion head according to this invention.

Fig. 11 is a partial view in cross section of an annular die according to the invention.

30 DESCRIPTION OF THE PREFERRED EMBODIMENT

As shown in Fig. 7, one embodiment of an extrusion head, indicated generally at 10, in accordance with the invention includes one or more extrusion modules such as a plurality of extrusion modules indicated generally

at 14, 16, 18 and 20 which receive streams of different polymer materials from respective conventional screw extruders 24, 26, 28, and 30 for forming a multilayer parison 32 which is then extruded into a container blow mold as illustrated in Fig. 10. As shown in Fig. 1, the modules 14, 16, 18 and 20 are coaxially mounted in spaced relationship along the axis 22 of the modules so as to form air spaces 88 including frustoconical air spaces 90 thermally isolating each module in the head to enable improved extrusion temperature control of each layer being extruded.

In the illustrated parison head, the modules 14, 16, 18 and 20 coaxially extend over spaced sections of a tapered stepped mandrel 34 so as to extrude their respective layers into a tubular extrusion channel 36 defined between the inner surfaces of the modules and the outer surface of the mandrel.

The modules 14, 16, 18 and 20 have substantially similar constructions. As shown in Fig. 3 for the module 18, each of the modules includes upper and lower members 40 and 42 which mate together and include a plastic material inlet 46 opening on the periphery of the module, an annular outlet 48 opening at the inner surface of the module, and one or more spiral channels such as a pair of spiral channels 50 and 51, Figs. 2 and 3, extending from bifurcated inlet channels 52 and 53 to a position adjacent to the outlet 48. The inlet 46 is formed by machining the mating surfaces of the members or by boring along the parting line between the outer portions of the members. Alternatively, the inlet 46 can be formed by boring in one of the members 40 or 42 similar to that shown in U.S. Patent 4,798,526. The inlet bifurcated channels 52 and 53 are machined in opposite directions through ninety degree

arcs in the mating surfaces of the outer flange portions of the members 40 and 42. The mating flat or land surfaces of the flange portions of the members 40 and 42 sealingly engage each other to close the channels 52 and 53.

Center portions 54 and 56 of the members 40 and 42 are generally frustoconical with apexes extending downstream. As shown in Fig. 6, the inside surface of the center portion 56 has a cylindrical ring portion 58 and three successive frustoconical portions 60, 61 and 62 which extend inward from the ring portion 58 to the cylindrical surface 63 of a bore which defines a portion of the outer wall of the tubular extrusion channel 36, Fig. 1. The slant angle of the surface 61, i.e., the angle of the surface 61 relative to the axis 22, is less than the slant angle of the surfaces 60 and 62 so that the thickness of an annular frustoconical space or passage 64, Fig. 4, between the portions 54 and 56 gradually increases over the region of the spiral channels 50 and 51, as illustrated by the short and long dashed line 70 which has the same angle as surfaces 60 and 62. As shown in Fig. 5, the outside surface of the inner frustoconical portion 54 has a cylindrical ring portion 65 sealingly engaging the surface 58, a first frustoconical surface portion 66 extending inward from the ring portion 65 to the first convolution of the spiral channels 50 and 51, and a second frustoconical surface portion 67 extending inward from the outermost spiral convolution formed by channels 50 and 51 to the apex of the frustoconical portion 54 where a cylindrical surface 68 of above, Fig. 4, defines a portion of the outer wall of the tubular extrusion channel 36. The bores defining cylindrical surfaces 63 and 68 are coaxial. Edges 71,

Fig. 2, between the first and second frustoconical surfaces 66 and 67 are formed in the land areas between the first convolutions of the spiral channels 50 and 51. The first frustoconical surface portion 66 has a
5 slant angle equal to surface 60 so that surface portion 66 sealingly engages the surface portion 60. The second frustoconical surface portion 67 also has the same slant angle as surfaces 60 and 66 but has a reduced diameter, as illustrated by the long and short
10 dashed line 69 which is an extension of the surface 66, so as to introduce an initial frustoconical space or thickness between the surface 61 and the land areas separating the spiral channels 50 and 51 to begin the frustoconical passage 64. At its inner end the
15 frustoconical passage 64 defines the outlet 48.

Referring to Fig. 2, the inlet channels 52 and 53 have extensions 72 and 73 machined in the surfaces 65 and 66 of the inner center portion 54 to open into the origins of the respective spiral channels 50 and 51.
20 these origins are on opposite sides, 180° apart. The spiral channels 50 and 51 are formed by machining the frustoconical surface 67 of the inner frustoconical portion 54 and each extend clockwise for approximately one and one-half convolutions about the frustoconical
25 portion 54. The cross-sectional area of each channel 50 and 51 gradually decreases from its origin to its endpoint so that the polymer forced into each channel at its origin is gradually dispersed into the increasing width of the frustoconical passage 64 to
30 distribute the polymer evenly about the frustoconical portion 54. The pitch of the spiral channels, i.e., the spacing between adjacent convolutions, is constant and the depth of the spiral channels relative to

surface 67 changes linearly so as to facilitate the machining of the channels.

The length of the spiral channels must together circumscribe or extend symmetrically around the longitudinal axis of the extrusion module or modules, i.e., extend substantially 360° around the axis of the bore which the mating inner and outer portions create to form extrusion channel 36, so as to subject all of the polymer flowing from the inlet to the outlet to substantially the same process conditions.

"Circumscribe," as used herein, is meant to include circular as well as non-circular paths. Such channels provide a means whereby the polymer is distributed at the annular extrusion outlet with properties which are substantially symmetrical around the axis of the extrusion module or modules for all resin which is distributed through the outlet.

In the modification shown in Fig. 8, channels 93 and 94 extend in opposite directions each through a minimum of 180° along spiral paths so that the channels 93 and 94 together extend completely around the inner frustoconical portion. The numbers of spiral channels and their direction can vary. The modification of Fig. 9 illustrates a single spiral channel 96 which makes more than three full convolutions around the inner frustoconical portion.

Referring back to Fig. 3, the outside surface 76 of the lower portion of the lower frustoconical portion 56 has a slant angle which is less than the slant angle of the inside surface 78 of the upper frustoconical portion 54 so that the width 82 of the inside surface of the module 18 along the axis 22 is greater than the width 86 of the outer portions of the module 18. The difference between the widths 82 and 86 is selected to

provid the desired spacing 88, Fig. 1, between adjacent modules. The lower edge of the apex of each higher module 14, 16 and 18 engages the upper side of the next lower module 16, 18 and 20 to define the spacing 88 between modules. Spacers 84 formed on the bottom of the flanges of the lower members 42 abut the adjacent modules to assist in maintaining even spacing between the flanges or outer portions of the modules around their circumference. These spacers 84 are broken by the various bores into the flange so as to permit air flow into and out of the spaces 88. The frustoconical air space portions 90 of the spaces 88 extend to the points of engagement between modules.

Bolts 98, Figs. 1 and 2, secure the upper and lower members 40 and 42 of the extrusion modules 14, 16, 18 and 20 together. Guide pins 99, Figs. 2 and 4, provide for proper alignment of the members 40 and 42 during assembly. Threaded bores 101, Fig. 6, in the members 42 are aligned with recesses 103, Figs. 2 and 5, in the members 40 so that conventional jacking bolts (not shown) can be screwed into the bores 101 to engage the recesses and force the members 40 and 42 apart during disassembly.

As shown in Fig. 1, the modules 14, 16, 18 and 20 are held in the extrusion head 10 by upper and lower clamp members 100 and 102 and by bolts 104, see also Fig. 2, which extend through bores in the clamp members and the extrusion modules. The lower surface 106 of the upper clamp member 100 has a convex frustoconical configuration similar to the lower surface of the extrusion modules 14, 16, 18 and 20, and the upper surface 108 of the lower clamp member 102 has a concave frustoconical configuration similar to the upper surface of the extrusion modules. This enables

extrusion modules to be interchanged in position as well as the clamp members to be used to hold a single extrusion module or any number of modules.

5 The mandrel 34 is tubular and extends through the upper clamp member and a mounting plate 110 fastened by bolts 112 to the upper clamp member 100. Bolts 113 secure the mounting plate 110 to conventional blow molding and supporting structures (not shown). A threaded nut 114 secures the upper end of the mandrel
10 which has a tapered fit in the clamp member 100. The mandrel 34 is tapered downward with by a plurality of successive steps 118, 120, 122 and 124 which begin at each corresponding outlet of the modules 14, 16, 18 and 20 to provide for the extrusion of the successive
15 polymer layers on the mandrel. The diameters of each step are selected in accordance with the desired thickness of the corresponding layer being extruded. Generally different mandrels are required for different arrangements of extrusion modules.

20 Alternatively, the mandrel can have a constant diameter through the extrusion modules and the inner diameters of the extrusion modules can be stepped. This limits the interchangeability of the modules, but blank modules can be manufactured with the inner
25 diameters machined later after the extrusion head configuration is determined.

Annular upper and lower dies 128 and 130 are mounted by a die clamp 132 and bolts 136 and 138 on the bottom of the module clamp member 102. The lower die
30 130 is threaded to the upper die 128. Positioned within the dies is a die core 140 which is threaded onto the lower end of a shaft 142 slidably extending through the lumen of the mandrel 34. The die 128 has its die opening tapered or stepped down in diameter at

144 in correspondence to the tapered terminal end of the mandrel 34 so that a constant cross-sectional area of the extrusion passage is maintained. This reduced diameter extends along a section 146 of constant diameter through the upper portion of the lower die 130 with the bottom portion 148 of the lower die flaring out to the desired diameter of the article or parison. The bottom portion 150 of the die core 140 flares outwardly at an angle slightly greater than the angle of the die portion 148 so that the exit thickness of the annular extrusion channel is less than the upper portion of the extrusion channel to insure that the layers of plastic polymer are firmly bonded together and that the cross-sectional area of the extrusion passage is maintained.

In order to assure that the polymer layers are preferably radially compressed to some degree upon being extruded from the die, the cross-sectional area of the annular channel at the exit from the bottom of the die portions 148 and 150 is slightly less than the cross-sectional area at the entrance portion of the channel. In other words, the extruded multi-layer polymer structure is preferably compressed slightly by reason of the reduction in the cross-sectional area of the flow passage formed by the channel formed by the elements 148 and 150 in the direction of the exit therefrom. This assures compression of the multi-layer structure as it exits from the die and provides firm bonding and enhanced structural integrity of the extruded multi-layer parison.

As illustrated in Fig. 11 the bottom portion 150 of the die core 140 can alternatively flare inwardly at an angle greater than the angle of the die portion 148. As a result the die is inwardly tapered, but has an

expanding extrusion channel annulus. In the embodiment of Fig. 11, the same contraction in cross-sectional area of the annular flow passage is preferably provided in order to compress the extruded multi-layer structure as it exits the die.

A center longitudinal bore 152 is formed through the die core 140 and the shaft 142 for passing gas into the parison being extruded to prevent collapse of the parison.

The extrudate exits the above-described die into a container blow mold according to conventional techniques. As illustrated in Fig. 10 parison 32 exits into a container blow mold 200. Container blow mold 200 can be a conventional split mold which is divided into halves 200a and 200b along its longitudinal axis and has a shape selected for the particular container desired. The extruded parison 32 is then processed according to conventional blow molding techniques. See, for example, "Blow Molding", Modern Plastics, October 1991, pp. 222-224.

For example, after parison 32 exits into container blow mold 200 halves 200a and 200b of the mold come together, thereby pinching the bottom of parison 32 to form a seal. The sealed bottom of the parison will become the bottom of the finished container. Shortly after the bottom of the parison is pinched, a conventional cutting blade (not shown) severs the parison from the extrudate exiting the annular die 130. The container blow mold 200 is then removed from under annular die 130 and replaced with another mold 300 to repeat the process described above. This particular process is known as a single-station shuttle process.

After the container blow mold is removed from under extrusion head 10, container blow mold 200 is

shuttled to calibration station 310. A blow pin 311 is then inserted into container blow mold 200 and parison 32 to inflate the parison into a container schematically illustrated as 312 in figure 10.

5 Container blow mold 200 is not illustrated at calibration station 310 in order to better illustrate container 312. The blown container 312 is then separated from mold 200 and trimmed using standard techniques.

10 As shown in Fig. 7, the illustrated parison extrusion apparatus includes a conventional control 160 which controls the vertical position of the shaft 142 in the mandrel 34. Parisons being extruded are often varied in thickness from the bottom to the top; i.e.,
15 bottle bottom portions having inverted bottoms need thicker walls at the bottom to prevent bulging of the bottoms from the pressure of the bottle contents such as a carbonated beverage. Additionally the control 160 can vary the extrusion pressures of the extruders 24,
20 26, 28 and 30 to vary the thickness of each layer being extruded relative to the other layers in a conventional manner. For example, the thickness of a barrier layer can be maintained uniform throughout the bottle height while the thickness of a structural layer is reduced in
25 upper portions of the bottle.

Referring back to Fig. 1, electrical heater coils 164, 166, 168, 170, 172, 174, 175 and 176 are mounted on the extrusion modules 14, 16, 18 and 20, the clamp members 100 and 102 and the lower die member 130,
30 respectively, for initially heating the corresponding members to their desired operating temperatures as well as maintaining a proper temperature during operation. Thermocouple sensing elements 180, 182, 184, 186, 188 and 190 provide temperature signals of the extrusion

modules 14, 16, 18 and 20, the lower clamp 102, and the die member 130 to conventional control circuitry (not shown) operating the heater coils.

5 In an example of a parison suitable for blow molding to form a bottle, the parison is formed by extruding inner and outer layers of polycarbonate, and intermediate layers of amorphous polyamide and regrind through multiple extrusion modules. However, there may be instances where a single material has properties
10 which meet all of the requirements of a particular container application. In those instances, parisons having only one layer are needed. Accordingly, those single-layered parisons can also be prepared into single-layered containers according to the invention
15 wherein only one extrusion module would be used.

The described embodiment has several advantages over the prior art extrusion apparatus. The spiral channel or channels forming together at least one full convolution gradually opening into the frustoconical
20 passage 64 results in pressure differentials in the channel or channels being cancelled by pressure differentials in the thinner upper portions of the frustoconical passage 64. This eliminates the need for an annular pressure equalization and distribution
25 chamber which is generally required in prior art tubular article extrusion apparatus. Such equalization and distribution chambers still have some unequal pressure, i.e., there must be a pressure differential to produce plastic polymer flow from one side to the
30 other side of the annular chamber. The uneven pressure around the annular outlet produces uneven thicknesses in the layers being formed in the parison. Thus the embodiments of Figs. 1-9 produce superior circumferential layer thickness uniformity.

Furthermore a generally restrictive frustoconical transfer passage extends from the prior art equalization and distribution chamber to the annular outlet in order to minimize the pressure differential in the equalization and distribution chamber. This prior art restrictive transfer passage results in a requirement for a substantially higher melt pressure compared to the present embodiment which relies upon at least one convolution formed by a channel or by the combined length of two or more channels of decreasing cross section opening into the gradual increasing thickness of the frustoconical passage 64 to minimize circumferential pressure differentials at the outlet 48. The size of the spiral channel or channels and the thickness of the passage 64 are selected to produce substantially less pressure drop between the inlet 46 and outlet 48 compared to the prior art.

Still further the elimination of the prior art equalization chamber with its opening into a restrictive frustoconical transfer passage reduces shear on the plastic polymer that is produced by such opening. Substantially less shear results from the present gradual opening of the spiral channel or channels through one or more spiral convolutions in the frustoconical passage 64. This results in increased strength in the article being produced.

Circumferential polymer extrusion temperatures tend to be more uniform in extrusion heads according to the invention, and substantially more uniform in the embodiments having two or more spiral distribution channel convolutions. As discussed earlier, since polymer melt in the prior art flows from the inlet side of the equalization and distribution chamber to the opposite side, a temperature differential can be

produced where the inlet polymer melt temperature differs from the average temperature of the distribution module. As a result, the actual and latent internal stresses discussed above occur.

5 However, in extrusion heads according to this invention all portions of the polymer material flowing from the inlet to the annular extrusion channel are exposed to substantially the same process conditions, e.g., temperature, pressure, shear, etc., along the channel
10 means from the inlet to the annular extrusion channel. Therefore, all of the polymer arriving at the annular extrusion channel has substantially the same process history, that is a substantially identical prior exposure to such process conditions, and is therefore
15 substantially uniform in its properties around the periphery of the extrusion channel as it is extruded therefrom. Thus, the tendency for circumferential temperature differentials and the occurrence of non-homogeneities are reduced.

20 Reducing the occurrences of non-homogeneities allows one to produce parisons and bottles which are believed to be superior to those in the art. As indicated earlier, reducing non-homogenous distribution of resin which result from pressure and temperature
25 differentials, as well as other processing differentials, reduces the number of actual and latent internal stresses in any parison, bottle or like article prepared from the resin. Accordingly, the resulting bottle or like article will possess superior
30 ability to maintain its integrity under external stresses.

The term "properties" as used herein refer to those properties which are the result of process conditions applied to the resin during the flow from

the inlet to the outlet. These include such parameters as process temperatures, pressures, shear conditions and other process conditions to which the polymer is exposed along the path of flow from the inlet to the annular extrusion outlet. The flow path is arranged symmetrically around the periphery of the axis of the module(s) so that all of the polymer is exposed to substantially the same process conditions during its flow from the inlet to the extrusion outlet, with the result that it arrives at the extrusion outlet with substantially symmetrical and homogenous properties around the full periphery of the extrusion outlet.

The present embodiment also provides greater temperature isolation between adjacent modules with a relatively simple and inexpensive structure. The prior art included abutting collars for spacing modules, but the collars had substantial thickness to transfer heat between modules. The present embodiment by including frustoconical air spaces 90 provides improved temperature isolation between extrusion modules.

Still further, the die output structure with section 144 reducing the annular extrusion channel diameter followed by the section 146 of uniform diameter and then the section 148 producing an increase in diameter to the desired container or parison diameter, results in improved product by eliminating prior art tendencies for failure of multiple layers to adhere uniformly together.

While the described embodiment is directed to manufacture of parisons used for blow molding bottles, the disclosed modular extrusion head is suitable for the manufacture of many other tubular articles such as film which is formed by slitting a tubular form with or without blowing of the tubular form; pipe or other

elongated profile article which may or may not be filled with foam such as through bore 152; glass mat reinforced sheet wherein polymer is extruded from one or more annular extrusion heads with rectangular center bores onto a glass fiber mat; pultruded sheet, rod or profile article; and wire coatings. For certain applications such as forming wire coatings or extruding coatings on other elongated materials, the extrusion head does not include a mandrel; rather the object on which the coatings are being extruded take the place of the mandrel. The term "container" is used herein to include all of the above described articles.

The container of the present invention is remarkably superior to those formed by prior art methods in that it is relatively free from residual internal stresses otherwise carried forward from the parison by reason of the fact that the polymers of which such prior art parisons were formed were subjected to non-uniform processing conditions in the extrusion head. These non-uniform conditions resulted from the fact that flow paths from the inlets of such prior art extrusion apparatus were non-symmetrical in flow patterns from the inlets to the annular extrusion channel. In the apparatus and method of the present invention, such flow paths extend symmetrically about the axis of each module such that all of the polymer flowing from the inlet to the extrusion channel is subjected to substantially the same process conditions, whereby the properties of the polymer are substantially the same and homogeneous around the full periphery of the annular extrusion channel at the point of extrusion from the channel.

The parison thus formed is therefore substantially free from residual internal stresses that would

otherwise occur as a result of such non-uniformities and non-homogeneities. The same advantages are realized whether the container is formed from a single layer or from a plurality of layers in accordance with the present invention. In either case, the finished container is substantially free from residual internal stresses which would otherwise be present from the formation of the parison. It is thus believed that the finished container of this invention can be effectively and safely reused or reclaimed.

The above described embodiment is only illustrative of the disclosed embodiment and many other embodiments, variations, modifications, and changes in detail can be devised without departing from the scope and spirit of the invention as defined in the following claims.

- 27 -

WHAT IS CLAIMED IS:

1. A polymer material extrusion head for extruding
containers comprising
one or more annular extrusion modules disposed
along a longitudinal axis of the module or modules;
means for holding the annular extrusion module or
modules along the axis;
the extrusion module or modules each having a
polymer inlet, a bore having an inner cylindrical
surface, and an annular extrusion outlet opening into
the inner cylindrical surface;
each of said module or modules having channel
means for receiving and distributing polymer extending
from the inlet to the outlet and defining a flow path
for the polymer to flow from the inlet to the annular
extrusion outlet through which the polymer is extruded
in annular form, said channel means extending
symmetrically around the longitudinal axis of said
extrusion module or modules in a manner so as to
subject all of the polymer flowing from said inlet to
said extrusion outlet to substantially the same process
conditions along said flow path whereby the polymer is
distributed at the annular extrusion outlet with
properties which are substantially symmetrical around
the axis for all resin distributed through said outlet.
2. A polymer resin extrusion head as defined in
claim 1 wherein the channel means includes one or more
spiral flow paths in the annular extrusion module or
modules wherein the one or more flow paths
substantially circumscribes the axis and which
gradually opens into an annular frustoconical space to
distribute the resin into the outlet.

- 28 -

3. A polymer resin extrusion head as defined in
2 claim 1 wherein the channel means comprises two spiral
flow paths, each path originating from said inlet and
4 each path extending in an opposite direction for at
least 180° around the axis so that the axis is
6 substantially circumscribed by the two paths.

4. A polymer resin extrusion head as defined in
2 claim 3 wherein each of the two spiral paths
substantially circumscribes the axis of the extrusion
4 module or modules so that one path is substantially
concentric with the other path.

5. An extrusion head according to claim 1
2 wherein the channel means circumscribes the axis along
more than one spiral path.

6. A polymer resin extrusion head as defined in
2 any one of claims 1-5 wherein the channel means has a
cross-section which decreases from the inlet to the
4 outlet and the channel means gradually opens into an
annular frustoconical space which opens into the
6 outlet.

7. A polymer resin extrusion head as defined in
2 claim 6 wherein the annular frustoconical space
increases in thickness as the space opens into the
4 outlet.

- 29 -

8. A polymer resin extrusion head for extruding
2 containers comprising
one or more annular extrusion modules disposed
4 along an axis of the module or modules;
means for holding the annular extrusion module or
6 modules along the axis each extrusion module or modules
having a pair of mating coaxial annular members, and
8 means securing the pair of mating annular members
together;
10 the pair of mating annular members defining a
resin inlet on the periphery of the module, a coaxial
12 bore having an inner cylindrical surface, an annular
extrusion outlet opening into the cylindrical surface;
14 each pair of mating annular members having channel
means formed on mating surfaces of the mating annular
16 members for receiving and distributing resin from the
inlet to the annular extrusion outlet and defining a
18 flow path for the polymer to flow from the inlet to the
annular extrusion outlet through which the polymer is
20 extruded in annular form, said channel means extending
symmetrically around the longitudinal axis of said
22 extrusion module or modules in a manner so as to
subject all of the polymer flowing from said inlet to
24 said extrusion outlet to substantially the same process
conditions along said flow path whereby the polymer is
26 distributed at the annular extrusion outlet with
properties which are substantially symmetrical around
28 the axis for all resin distributed through said outlet;
the pair of mating members having inner and outer
30 nested frustoconical portions, respectively, with the
annular extrusion outlet defined by an annular space
32 between the frustoconical portions; and
the inner frustoconical portion having an inside
34 surface with a greater angle from the axis than the
angle of an outside surface of the outer frustoconical
36 portion.

- 30 -

9. A polymer resin extrusion head as defined in
2 claim 8 wherein the channel means includes one or more
spiral paths extending completely around the inner
4 frustoconical portion and gradually opening into the
annular frustoconical space between the frustoconical
6 portions to distribute the resin around the inner
frustoconical portion and into the annular extrusion
8 outlet.

10. A polymer resin extrusion head as defined in
2 claim 9 wherein the frustoconical portions have mating
surfaces defining a frustoconical space with an
4 increasing thickness toward the apexes, and the spiral
paths gradually open into the frustoconical space
6 progressively toward the apexes.

11. A polymer resin extrusion head as defined in
2 claim 10 wherein the mating surfaces of the
frustoconical portions have base sections in sealing
4 engagement with each other, and the mating surfaces
defining the frustoconical space extend from the base
6 sections to the apexes of the frustoconical portions
with the increasing thickness of the frustoconical
8 space being formed over a region containing the spiral
path.

12. A polymer resin extrusion head as defined in
2 claim 11 wherein the frustoconical space between the
frustoconical portions is initially determined by a
4 reduction in diameter of the inner frustoconical
portion downstream from a first convolution of the
6 spiral channel, and the increasing thickness of the
frustoconical space is formed by a frustoconical
8 surface portion on the inside of the outer
frustoconical portion having a slant angle less than a
10 slant angle of the surface of the inner frustoconical
portion over the region of the spiral path.

- 31 -

13. A polymer resin extrusion head as defined in
2 claim 8 including a mandrel; and wherein the extrusion
head comprises a plurality of annular extrusion modules
4 which are spaced longitudinally along the mandrel.

- 32 -

14. A polymer resin extrusion head for extruding
2 multilayer containers comprising
a plurality of coaxial annular extrusion modules;
4 means for holding the modules spaced
longitudinally along the axis of the modules;
6 each module having a pair of mating coaxial
annular members, and means securing the pair of mating
8 annular members together;
the pair of mating annular members defining a
10 resin inlet on the periphery of the module, a coaxial
bore having an inner cylindrical surface, an annular
12 extrusion outlet opening into the cylindrical surface;
each of said module or modules having channel
14 means for receiving and distributing polymer extending
from the inlet to the outlet and defining a flow path
16 for the polymer to flow from the inlet to the annular
extrusion outlet through which the polymer is extruded
18 in annular form, said channel means extending
symmetrically around the longitudinal axis of said
20 extrusion module or modules in a manner so as to
subject all of the polymer flowing from said inlet to
22 said extrusion outlet to substantially the same process
conditions along said flow path whereby the polymer is
24 distributed at the annular extrusion outlet with
properties which are substantially symmetrical around
26 the axis for all resin distributed through said outlet.
each module further having a center portion which
28 is frustoconical wherein the frustoconical center
portion at the center bore has a dimension along the
30 axis which is greater than the axial dimension of the
outer portions of each module so that the apex of each
32 preceding module engages the succeeding adjacent module
to form air spaces including frustoconical air space
34 portions between adjacent modules to produce enhanced
temperature isolation between modules.

- 33 -

15. A polymer resin extrusion head for extruding
2 multilayer containers comprising
an elongate mandrel;
4 a plurality of coaxial annular extrusion modules
spaced longitudinally along the mandrel and extending
6 around successive sections of a mandrel so as to define
a tubular extrusion channel between the modules and the
8 mandrel for receiving successive layers extruded by the
modules into the tubular extrusion channel;
10 an annular die mounted downstream from the
extrusion modules and having three successive sections
12 for receiving and forming the multilayered tubular
extrusion from extrusion channel, the first section
14 having a tapered diameter progressively reduced from
the diameter of the annular extrusion channel, the
16 second section having a constant diameter equal to the
exit diameter of the first section throughout its
18 length, and the third section having a flared diameter
progressively increasing the diameter from the diameter
20 of the second section to a desired diameter.

- 34 -

16. A process for forming containers from polymer
2 materials comprising:
disposing and securing an extrusion module or
4 modules along a longitudinal axis;
said extrusion module or modules each having a
6 resin inlet, a bore having an inner cylindrical
surface, and an annular extrusion outlet opening into
8 said inner cylindrical surface;
each of said module or modules having channel
10 means for receiving and distributing resin extending
from the inlet to the outlet and defining a flow path
12 for the polymer to flow from the inlet to the annular
extrusion outlet through which the polymer is extruded
14 in annular form, said channel means extending
symmetrically around the longitudinal axis of said
16 extrusion module or modules in a manner so as to
subject all of the polymer flowing from said inlet to
18 said outlet to substantially the same process
conditions along said flow path whereby the polymer is
20 distributed at the annular outlet with properties which
are substantially symmetrical around the axis for all
22 resin distributed through the outlet;
introducing a polymer material into said inlet and
24 flowing said polymer through the module or modules from
the inlet and through said flow path to said extrusion
26 outlet so that the flowing polymer material
substantially circumscribes the axis and arrives at the
28 extrusion outlet with properties which are
substantially symmetrical around the axis for all
30 polymer flowing through the module or modules;
extruding the polymer material through said
32 extrusion outlet;
forming a parison from the polymer material as it
34 exits an extrusion channel, and
molding a container from the parison so formed,
36 whereby said container is formed substantially free of

- 35 -

internal stresses which otherwise result from
38 peripheral variations in the properties of the extruded
polymer around the periphery of said parison.

17. A process as defined in claim 16 comprising
2 introducing a polymer material into said inlet and
flowing said polymer through the module or modules from
4 the inlet and through said flow path to said extrusion
outlet so that the flowing polymer material
6 substantially circumscribes the longitudinal axis of
said module or modules in one or more spirals.

18. A process as defined in claim 16 comprising
2 introducing polymer material into said inlet and
flowing said polymer to the the extrusion outlet so
4 that the flowing polymer flows in two opposite
directions for at least 180° around the longitudinal
6 axis in each direction, with both polymer flows
arriving at the extrusion outlet.

19. A process as defined in claim 18 comprising
2 flowing polymer in one or more spirals for each
direction.

20. A process as defined in claim 16 further
2 comprising flowing the polymer material through an
annular frustoconical space prior to delivering the
4 resin to the extrusion outlet.

21. A process as defined in claim 20 comprising
2 flowing the polymer material from the inlet to the
annular frustoconical space along a path having a
4 cross-section which decreases as the path approaches
the annular frustoconical space.

22. A process as defined in claim 21 comprising
2 flowing the resin material through an annular
frustoconical space which increases in thickness as the
4 annular frustoconical space opens into the extrusion
channel.

23. A container prepared by any one of the
2 process s in claims 16-22.

- 36 -

24. A container as defined in claim 23 comprising
2 a single layer extruded from a single extrusion module.

- 37 -

25. A polymer resin extrusion head for extruding
2 tubular articles, comprising
one or more annular extrusion modules disposed
4 along an axis of the module or modules;
upper and lower clamp members being disposed on
6 opposite sides of the extrusion module or modules along
the axis;
8 means securing the annular extrusion module or
modules between the upper and lower clamp members;
10 said extrusion module or each module having a pair
of mating coaxial annular members, and means securing
12 the pair of mating annular members together;
said pair of mating annular members defining a
14 resin inlet on the periphery of the module, a coaxial
bore, an annular extrusion outlet opening into the
16 cylindrical surface of the bore, and channel means
formed on mating surfaces of the annular members for
18 receiving and distributing resin from the inlet to the
outlet;
20 said pair of mating members having inner and outer
nested frustoconical portions, respectively, with the
22 outlet defined by an annular space between the
frustoconical portions;
24 said inner frustoconical portion having an inside
surface with a greater angle from the axis than the
26 angle of an outside surface of the outer frustoconical
portion;
28 said upper and lower clamp members having
respective convex and concave frustoconical surfaces
30 with angles less than and greater than, respectively,
the inside surface of the inner frustoconical portion
32 and the outside surface of the outer frustoconical
portion so that the apex of the convex frustoconical
34 surface of the upper clamp member abuts the inside
surface of the inner frustoconical portion of the
36 module or the uppermost module and the outside surface

- 38 -

of the apex of the outer frustoconical portion of the
38 outer frustoconical portion of the module or the
lowermost module abuts the concave frustoconical
40 surface of the lower clamp member to form air spaces
between the module or modules and the upper and lower
42 clamp members including frustoconical air space
portions.

26. A polymer resin extrusion head as defined in
2 claim 25 wherein the channel means includes one or more
channels extending spirally in the outer surface of the
4 inner frustoconical portion to form spiral channel
means extending completely around the inner
6 frustoconical portion and gradually opening into the
annular frustoconical space between the frustoconical
8 portions to distribute the resin around the inner
frustoconical portion and into the outlet.

27. A polymer resin extrusion head as defined in
2 claim 26 wherein the frustoconical portions have mating
surfaces defining a frustoconical space with an
4 increasing thickness toward the apexes, and the spiral
channel means gradually open into the frustoconical
6 space progressively toward the apexes.

28. A polymer resin extrusion head as defined in
2 claim 27 wherein the mating surfaces of the
frustoconical portions have base sections sealing
4 engaging each other, and the mating surfaces defining
the frustoconical space extend from the base sections
6 to the apexes of the frustoconical portions with the
increasing thickness of the frustoconical space being
8 formed over a region containing the spiral channel.

- 39 -

29. A polymer resin extrusion head as defined in
2 claim 28 wherein the frustoconical space between the
frustoconical portions is initially determined by a
4 reduction in diameter of the inner frustoconical
portion downstream from the first convolution of the
6 spiral channel, and the increasing thickness of the
frustoconical space is formed by a frustoconical
8 surface portion on the inside of the outer
frustoconical portion having a slant angle less than a
10 slant angle of the surface of inner frustoconical
portion over the region of the spiral channel.

30. A polymer resin extrusion head as defined in
2 claim 25 including a plurality of the annular extrusion
modules spaced longitudinally along the axis so as to
4 form air spaces including frustoconical air space
portions between adjacent modules to reduce direct heat
6 transfer between adjacent modules.

31. A polymer resin extrusion head as defined in
2 claim 26 including a plurality of the annular extrusion
modules spaced longitudinally along the axis so as to
4 form air spaces including frustoconical air space
portions between adjacent modules to reduce direct heat
6 transfer between adjacent modules.

32. A polymer resin extrusion head as defined in
2 claim 27 including a plurality of the annular extrusion
modules spaced longitudinally along the axis so as to
4 form air spaces including frustoconical air space
portions between adjacent modules to reduce direct heat
6 transfer between adjacent modules.

33. A polymer resin extrusion head as defined in
2 claim 28 including a plurality of the annular extrusion
modules spaced longitudinally along the axis so as to
4 form air spaces including frustoconical air space
portions between adjacent modules to reduce direct heat
6 transfer between adjacent modules.

- 40 -

34. A polymer resin extrusion head as defined in
2 claim 29 including a plurality of the annular extrusion
modules spaced longitudinally along the axis so as to
4 form air spaces including frustoconical air space
portions between adjacent modules to reduce direct heat
6 transfer between adjacent modules.

35. A polymer resin extrusion head as defined in
2 claim 30 including a mandrel; and wherein the plurality
of the annular extrusion modules are spaced
4 longitudinally along the mandrel.

36. A polymer resin extrusion head as defined in
2 claim 35 wherein the plurality of annular extrusion
modules have the same internal diameter, and the
4 mandrel has a plurality of successive sections with
progressively smaller diameters beginning at the
6 respective outlets of the annular extrusion dies.

- 41 -

37. A polymer resin extrusion head for extruding
2 multilayer tubular articles comprising
a plurality of coaxial annular extrusion modules;
4 means for holding the modules spaced
longitudinally along the axis of the modules;
6 each module having a pair of mating coaxial
annular members, and means securing the pair of mating
8 annular members together;
said pair of mating annular members defining a
10 resin inlet on the periphery of the module, a coaxial
bore, an annular extrusion outlet opening into the
12 cylindrical surface of the bore, and channel means
formed on mating surfaces of the annular members for
14 receiving and distributing resin from the inlet to the
outlet;
16 each module further having a center portion which
is frustoconical wherein the frustoconical center
18 portion at the center bore has a dimension along the
axis which is greater than the axial dimension of the
20 outer portions of each module so that the apex of each
preceding module engages the succeeding adjacent module
22 to form air spaces including frustoconical air space
portions between adjacent modules to produce enhanced
24 temperature isolation between modules.
38. A polymer resin extrusion head as defined in
2 claim 37 wherein the channel means includes one or more
channels extending spirally in the outer surface of the
4 inner frustoconical portion to form spiral channel
means extending completely around the inner
6 frustoconical portion and gradually opening into the
annular frustoconical space between the frustoconical
8 portions to distribute the resin around the inner
frustoconical portion and into the outlet.

- 42 -

39. A polymer resin extrusion head as defined in
2 claim 38 wherein the frustoconical portions have mating
surfaces defining a frustoconical space with an
4 increasing thickness toward the apexes, and the spiral
channel means gradually open into the frustoconical
6 space progressively toward the apexes.

40. A polymer resin extrusion head as defined in
2 claim 39 wherein the mating surfaces of the
frustoconical portions have base sections sealing
4 engaging each other, and the mating surfaces defining
the frustoconical space extend from the base sections
6 to the apexes of the frustoconical portions with the
increasing thickness of the frustoconical space being
8 formed over a region containing the spiral channel.

41. A polymer resin extrusion head as defined in
2 claim 40 wherein the frustoconical space between the
frustoconical portions is initially determined by a
4 reduction in diameter of the inner frustoconical
portion downstream from the first convolution of the
6 spiral channel, and the increasing thickness of the
frustoconical space is formed by a frustoconical
8 surface portion on the inside of the outer
frustoconical portion having a slant angle less than a
10 slant angle of the surface of inner frustoconical
portion over the region of the spiral channel.

42. A polymer resin extrusion head as defined in
2 claim 37 including a mandrel; and wherein the plurality
of the annular extrusion modules are spaced
4 longitudinally along the mandrel.

1/8





FIG. 1

2/8



3/8




FIG. 3






FIG. 4



SUBSTITUTE SHEET




FIG. 7

6/8




FIG. 8




FIG. 9

FIG. 10





FIG. 11



SUBSTITUTE SHEET

INTERNATIONAL SEARCH REPORT

PCT/US 91/08985

International Application No

I. CLASSIFICATION OF SUBJECT MATTER (If several classification symbols apply, indicate all) ⁶ According to International Patent Classification (IPC) or to both National Classification and IPC IPC ⁵ : B 29 C 47/06, B 29 C 49/04		
II. FIELDS SEARCHED Minimum Documentation Searched ⁷ Classification System Classification Symbols IPC ⁵ B 29 B, B 29 C, B 29 D Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ⁹		
Category ⁹	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
X	US, A, 4 522 775 (BRIGGS) 11 June 1985 (01.06.85), see column 4, lines 46-57; fig. 3.	1
A	---	8, 14- 16, 25, 37, 43
X	US, A, 4 649 004 (NOHARA) 10 March 1987 (10.03.87), see claims 1,7; fig. 2.	1
A	---	8, 14- 16, 25, 37
A	EP, A2, 0 215 337 (BATTENFELD FISCHER) 25 March 1987 (25.03.87), see claims; fig. 1.	1, 8, 14-16, 25, 37, 43
<p>¹⁰ Special categories of cited documents: ¹⁴</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Z" document member of the same patent family</p>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search 23 June 1992		Date of Mailing of this International Search Report 10 JUL 1992
International Searching Authority EUROPEAN PATENT OFFICE		Signature of Authorized Officer Mme N. KUIPER

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, " with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	EP, A2, 0 274 095 (BEKUM) 13 July 1988 (13.07.88), see the whole document. -----	1,8,43

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US91/08985 SAE 54666

In diesen Anhang sind die Mitglieder
der Patentfamilien der in obenge-
nannten internationalen Recherchenbericht
angeführten Patentedokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visée ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

In Recherchenbericht angeführtes Patentedokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A 4552775	12-11-85	WO A1 8300007	06-01-83
		AU A1 85823/82	18-01-83
		AU B2 546582	05-09-85
		DE C0 3262769	02-05-85
		EP A1 93720	16-11-83
		EP B1 93720	27-03-85
		AU A1 85830/82	18-01-83
		CA A1 1196809	19-11-85
		NO A 822055	23-12-82
		WO A1 8300006	06-01-83
US A 4649004	10-03-87	AU A1 37146/84	04-07-85
		AU B2 571917	28-04-88
		CA A1 1240113	09-08-88
		GB A1 2153739	29-08-85
		GB B2 2153739	26-08-87
		JP A2 60147306	03-08-85
		JP B4 3076645	06-12-91
		KR B1 9108615	19-10-91
		SE A0 8406622	27-12-84
		SE A 8406622	28-06-85
		US A 4741936	03-05-88
		GB A0 8432666	06-02-85
		JP A2 60137610	22-07-85
		JP B4 3067483	23-10-91
		ZA A 8410082	28-08-85
EP A2 215337	25-03-87	AT E 59332	15-01-91
		AU A1 62604/86	19-03-87
		AU B2 599048	12-07-90
		BR A 8604416	12-05-87
		CN A 86106753	20-05-87
		CN B 1009907	10-10-90
		DE A1 3532996	26-03-87
		DE C0 3676599	07-02-91
		EP A3 215337	21-09-88
		EP B1 215337	27-12-90
		JP A2 62066908	26-03-87
		US A 4889477	26-12-89
EP A2 274095	13-07-88	AT E 64336	15-06-91
		DE A1 3700237	21-07-88
		EP A3 274095	26-07-89
		EP B1 274095	12-06-91
		JP A2 63247009	13-10-88
		US A 4838778	13-06-89